

Dominion Sure Seal- Gravel Guard Application Instructions

SURFACE PREPARATION:

1. Remove all loose paint, rust and dirt from areas to be undercoated with wire brush. Repair rust.
2. Clean the area to be sprayed with DSS Sure Solv (BSS / 10058) or a high quality wax and grease remover.
3. Rusted metal should be repaired and treated with DSS Rust remover (BROG / 10045).
4. Lightly scuff bare metal areas that are to be treated.

APPLICATION:

1. If application is in a tight area or if over-spray is a concern, mask areas not to be coated.
2. Application : shake can vigorously for at least 3 minutes. Keep gun/can 12–18 inches from area being sprayed and pressure at 50-60 psi if applying with Schutz type gun .
3. Apply 2 or 3 even coats for full coverage. Apply by moving steadily and evenly.
4. Allow each coat to flash off for 5-10 minutes between coats.
5. Overspray can be cleaned up with DSS Sure Solv (BSS / 10058).
6. For many applications, Gravel Guard needs no further finishing. Allow of at least 1 ½ – 2 hours dry time before painting. Gravel Guard needs to be thoroughly dry before painting.

Dry time may vary depending on film build, temperature and air flow. A thicker coating will take longer.

Source: <https://dominionsureseal.com/product/gravel-guard/?v=5435c69ed3bc>